

CGM CIGIEMME S.p.A.



Controlli Non Distruttivi - Non Destructive Testing

Product Code 01024400 **Ref. no.** K755



MAGNETIC WET POWDER K 755

PRODUCT DESCRIPTION

K 755 is a fluorescent atomised magnetic powder used to prepare suspensions for wet magnetic particle testing.

K 755 powder can be suspended in a petroleum-based liquid vehicle (oil), such as Kerosenoil, or in water with the addition of a wetting agent (such as Ata Fluid A44 or Wetting Agent A38) to improve particle mobility, surface wettability and corrosion inhibition. The powder is characterised by medium/ small particle size and is therefore suitable for low to medium roughness surfaces.

K 755 is a product with low sulphur and halogen content, according to standards.

COMPOSITION

Iron oxides with high magnetic permeability and fluorescent pigments.

N.B.: As with all CGM products, the K 755 magnetic powder is tightly tested to ensure batch uniformity, optimal process verification and control reliability.

SPECIFICATIONS

- It can be suspended in oil or water.
- Excellent sensitivity.
- Excellent fluorescent contrast.
- Excellent particle mobility.
- Long-lasting particles.
- Easily dispersible.

PACKAGING TYPE

- 1 kg dosing containers

APPLICABILITY

Ideal for the detection of surface and sub-surface discontinuities such as:

- Inclusions.
- Straw.
 - Withdrawal cracks.
- Tears.
- Recalculations Folding.
- Flakes.
- Welding defects.
- Grinding cracks.
- Hardening cracks.
- Fatigue cracks.

ln:

- Semi-machined and machined parts.
- In-service inspections.
- Detection of small discontinuities.

INSTRUCTIONS FOR USE

TIP: always operate according to a procedure authorised by a 3rd level in Magnetic Particle Inspection.

- Prepare the magnetic suspension in oil or water with the addition of a wetting agent such as Ata Fluid A44 or Wetting Agent A38.





CGM CIGIEMME S.p.A.



Controlli Non Distruttivi - Non Destructive Testing

- Check, with the sedimentation glass tube, that the recommended concentration value is obtained.
- Ensure that the part to be inspected is clean to avoid false indications and contamination of the magnetic suspension.
- During use, keep the magnetic suspension stirring to ensure bath uniformity.
- Apply the magnetic suspension as required depending on the method chosen.

Continuous wet method

This is the method normally required by standards.

- Apply the magnetic suspension to all surfaces of the workpiece and simultaneously apply the magnetising current.
- Stop the application of the magnetic suspension before interrupting the current flow, so as not to wash away the indications.
- Leave to drain.
- Inspect the workpiece under ultra-violet light of the intensity required by standard/procedure.

Residual magnetism wet method

This method is only allowed in certain cases. Refer to the standard to be applied.

- Apply the magnetising current to the part to be inspected.
- Then apply the magnetic suspension.
- Leave to drain.
- Inspect the workpiece under ultra-violet light of the intensity required by standard/procedure.

With use, the dust content of the magnetic suspension tends to decrease and it is therefore necessary to check the strength of the bath daily using the sedimentation glass tube or the reference block, as stipulated in the inspection procedure. The bath must be replaced when it appears contaminated.

After the inspection and before final cleaning, it is advisable to demagnetise the inspected part to the residual magnetisation value specified in the inspection procedure. This also ensures easier removal of residual magnetic powder particles.

PROPERTIES AND PRODUCT COMPARISON

| | K 35 | K 40 | K 150 | K 755 | K 31-73 |
|--|-----------|---------------|-----------------|--------------------------|--------------------------|
| Colour ASTM E709 EN ISO 9934-2 | Black | Red | Dark green | Green | Green |
| Average particle size EN ISO 9934-2 | 1 μm | 9 μm | 12 µm | 8 µm | 3 µm |
| Solubility | 8-10 g/L* | 10 g/L* | 1.2 – 1.5 g/L** | 1.2% – 1.5 g/L** | 1.0 – 1.2 g/L** |
| Colour under UV light ASTM E709 EN ISO 9934-2 | NA | Bright orange | Emerald green | Yellow – Bright green | Yellow – Bright green |

Typical values.

^{**} The reported dilution guarantees that the bath complies with AMS 3044.



^{*} The reported dilution guarantees that the bath complies with AMS 3042.



CGM CIGIEMME S.p.A.



Controlli Non Distruttivi - Non Destructive Testing

RECOMMENDATIONS FOR THE USER

| NDT method | Fluorescent Magnetic Particle Inspection, wet method | | | |
|---|---|--|--|--|
| Shelf life | 3 years at a temperature between 5°C and 45°C, in a dry place out of direct sunlight | | | |
| Usage temperature | < 48°C | | | |
| Suspension vehicle | Kerosenoil or water | | | |
| Wetting agent for water baths | Ata Fluid A44 or Wetting Agent A38 | | | |
| Preliminary cleaning | Velnet/Solnet | | | |
| UV lamp | Labino | | | |
| Recommended accessories according to standards ASTM E1444 ASTM E709 EN ISO 9934-2 | Sedimentation glass tube – Magnetic stripe card type 2000 – Reference block type 1 (MTU) – Reference block type 2 – Flexible laminated strips – Tool Steel Ring type AS 5282 and type Ketos 01 – Octagonal plate | | | |

COMPLIANCE WITH STANDARDS

- ASME V Art. 7
- ASTM E709
- ASTM E1444
- EN ISO 9934-2
- MIL-STD-271
- NAVSEA 250-1500-1
- AMS 3044
- PMUC (certificate of conformity on request)

BENEFITS

- It forms clear and bright indications with minimal background fluorescence.
- It maintains the performance of the magnetic suspension over long periods of time thanks to high-quality pigments with good particle adhesion.

HEALTH AND SAFETY

Read all health and safety information before using this product. This information can be found in the Safety Data Sheet, available on request.

Rev. 06 - 29/05/2024

